

05 MAR 2003

10/526813

REC'D 08 OCT 2003

TIPO

PCT

P1 1073186

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office

October 03, 2003


THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/408,638

FILING DATE: September 05, 2002

RELATED PCT APPLICATION NUMBER: PCT/US03/27568

By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS



M. Sias

M. SIAS
Certifying Officer

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

09/05/02
1c849 U.S. PTO

Please type a plus sign (+) in this box →

+

09-09-02

60/40638 .000507 A.P.R.

SUBSTITUTE PTO/SB/16 (8-00)

Approved for use through 10/31/2002. OMB 0651-0032

Patent and Trademark Office. U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OBM control number

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR §1.53(c).

INVENTOR(S)					
Given Name (first and middle [if any])		Family Name or Surname		Residence (City and either State or Foreign Country)	
Gerald		Sugerman		Allendale, NJ	
<input type="checkbox"/> Additional inventors are being named on the <u>0</u> separately numbered sheets attached hereto.					
TITLE OF THE INVENTION (280 characters max)					
Fast Drying Coatings					
CORRESPONDENCE ADDRESS					
Direct all correspondence to:					
<input type="checkbox"/> Customer Number:		<div>Place Customer Number Bar Code Label Here</div>			
OR					
<input checked="" type="checkbox"/> Firm or Individual Name		Fish & Richardson P.C.			
Address		225 Franklin Street Boston, Massachusetts 02110-2804			
Country		United States	Telephone	(617) 542-5070	Fax (617) 542-8906
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification		Number of Pages	22	<input type="checkbox"/> CD(S), Number	
<input type="checkbox"/> Drawing(s)		Number of Sheets		<input type="checkbox"/> Other (specify)	
<input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76.					
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT (check one)					
<input checked="" type="checkbox"/> Applicant Claims small entity status. See 37 CFR 1.27.				FILING FEE AMOUNT (\$)	
<input checked="" type="checkbox"/> A check or money order is enclosed to cover the filing fees.				\$80.00	
<input type="checkbox"/> The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number:				06-1050	
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.					
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No.					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are:					

Respectfully submitted,

Signature

Name Jeffrey D. Hsi, Reg. No. 40,024

Date September 5, 2002

Telephone No. (617) 542-5070

Docket No. 14175-006P01
20502831.doc

CERTIFICATE OF MAILING BY EXPRESS MAIL

Express Mail Label No. EL 946112864

Date of Deposit September 5, 2002

60408438 .000502

Attorney's Docket No.: 14175-006P01

PROVISIONAL APPLICATION FOR PATENT
under
37 CFR §1.53(c)

TITLE: FAST DRYING COATINGS
APPLICANT: GERALD SUGERMAN

CERTIFICATE OF MAILING BY EXPRESS MAIL

Express Mail Label No EL 946112864

September 5, 2002
Date of Deposit

Fast Drying Coatings

BACKGROUND

Conventionally, lithographic (litho) inks, and varnishes have been designed to dry via combination of solvent evaporation and oxidative polymerization of unsaturated components.

5 Consequent to increasing concerns regarding the health, safety, and environmental impacts of volatile organic compounds, (VOCs); the contribution of this component (the evaporation of solvent is presently responsible for the major proportion of conventional litho inks' and varnish's drying speeds) to drying rates is anticipated to shrink in the future, as increasingly stringent limitations are placed on the usage of VOCs. Stacking of fresh prints in
10 order to conserve space, which is typical during long runs, frequently limits the efficacy of solvent evaporation as a drying mechanism. Additionally the incorporation of solvents in litho inks results in undesirable distortion (e.g., capillary spread prior to drying) of applied ink droplets (dot gain), thus limiting print resolution. The extent of dot gain beyond that consequent to the small proportion resulting from the mechanics of imperfect application of ink to a moving
15 substrate tends to be roughly proportional to the percentage of VOCs employed, hence solvent incorporation into litho ink formulations often limits print quality.

 The oxidative-polymerization component of the drying of present litho inks almost invariably requires acceleration by toxic heavy metals such as cobalt and manganese, and is often kinetically limited by oxygen availability, especially when printing on essentially non-
20 porous surfaces, and / or when fresh prints are stacked tightly, minimizing air access. A number of technologies have been developed to overcome drying rate limitations of conventional litho inks; these acceleration techniques include, the inclusion of various energy input systems, such as thermal energy (headset, and infrared drying), electron beam (EB), and ultraviolet (UV) radiation. The latter methodology typically requires incorporation of substantial proportions of
25 a combination of expensive, and often-toxic photo initiators, and related auxiliaries, in addition to the expensive hardware, intensive energy consumption, and radiation exposure hazards, implicit in the generation of short wave length radiation used in both EB and UV based curing systems.

US Patent No. 5,552,467 teaches the usage of thermally activated combinations of chemical reducing agents, and organic (hydro)peroxides, one placed in the ink and the other contained in fountain solution as a means of overcoming the oxidative-polymerization drying component rate limitations of heat set lithographic inks. The patent discloses the use of two-part systems that inherently exclude usage in single fluid inks, and is limited further limited by the reactivity of the components, resulting in relatively short shelf life of solutions and / dispersions of many organic (hydro)peroxides, and of reducing agents in unsaturated oil based vehicles, especially those containing carbon black an /or heavy metal based pigments, and in gum containing fountain solution concentrates. The specified technology has not been claimed to be effective for use in systems which must dry at/ or near ambient temperatures.

US Patent No. 5,173,113 teaches the utility of hydrogen peroxide as a fountain solution additive for the acceleration of drying of lithographic inks, by a factor of approximately twofold. This combination, however, is used as a two-part system, thus inherently precluding use in single fluid inks.

It has now been surprisingly found that the incorporation of moderate percentages of a combination of solutions of poly(hydroxy) aliphatic acid(s) in unsaturated fatty acids , and organic zirconium compounds, optionally in combination with multifunctional (meth)acrylate esters into otherwise conventional lithographic inks, and related vehicles and varnishes, both significantly enhances the drying rates of these inks and improves their flow. These materials have also been found to effectively utilize of low levels (10 to 5,000 parts per million (ppm) of organic (hydro)peroxides and / or of inorganic salts of peroxy acids, (cofactor reducing agents are thus not required) as replacements for the thermally activated organic (hydro)peroxide-reducing agent combination(s) and /or hydrogen peroxide as fountain solution additive drying accelerators, such as those described in US Patent No. 5,552,467, and US Patent No. 5,173,113, respectively.

SUMMARY

The invention relates to compositions, methods of making the compositions, and methods of using the compositions for coating applications. The coatings are suitable as inks, varnishes,

paints, and the like. In one aspect the coatings are fast drying, relative to existing technologies, and offer other advantages (e.g., print quality, color fastness, reduced or no VOC components, reduced or no toxic metal-containing components) useful in print and coatings applications.

The compositions of the invention incorporate moderate percentages of a combination of 2 to 15 weight percent of (10 to 35 wt.%) solutions of poly(hydroxy) aliphatic acid(s) in unsaturated fatty acids, and 0.4 to 4 weight % of organic zirconium compound(s), preferably in combination 1 to 7 weight % of multifunctional (meth)acrylate ester(s) into otherwise conventional lithographic inks, and related vehicles and varnishes.

In one aspect, the invention relates to a composition having unsaturated fatty acid solutions of one or more poly alpha (hydroxy)aliphatic acids, and less than 10 weight % of one or more multifunctional (meth)acrylate esters, vinyl ethers, or combinations thereof. The compositions can further include 0.4 to 4 weight % of one or more organic zirconium(4) compounds; one or more inorganic salts of peracids; 0.4 to 4 weight % of one or more organic zirconium(4) compounds and one or more inorganic salts of peracids; can include 2 to 15 weight percent of drying oil derived fatty acid solutions of 10-35 wt % of one or more poly alpha (hydroxy)aliphatic acid(s), 0.4 to 4 weight % of one or more organic zirconium(4) compounds, 1 to 7 weight % of one or more multifunctional (meth)acrylate esters, vinyl ethers, or combinations thereof, and catalytic proportions of one or more inorganic salts of peracids; or can include catalytic proportions of organic (hydro)peroxides; one or more additional ink vehicle or varnish components (e.g., solids, alkyds, polyesters or polyamides); or can have one or more compounds delineated in any of the tables herein (e.g., Tables A-D or 1-4).

Another aspect is a method of printing including using an ink having any of the compositions delineated herein, including those having unsaturated fatty acid solutions of one or more poly alpha (hydroxy)aliphatic acids, and less than 10 weight % of one or more multifunctional (meth)acrylate esters, vinyl ethers, or combinations thereof. The method can include applying the ink to a printing press; can be wherein the printing is lithographic printing; can be that wherein the printing includes printing on paper; or can involve any composition delineated herein having one or more compounds delineated in any of the tables herein (e.g., Tables A-D or 1-4).

In another aspect, the invention relates to a method of printing including using an ink vehicle or varnish having any of the compositions delineated herein, including those having

unsaturated fatty acid solutions of one or more poly alpha (hydroxy)aliphatic acids, and less than 10 weight % of one or more multifunctional (meth)acrylate esters, vinyl ethers, or combinations thereof. The method can be that wherein the ink vehicle or varnish is mixed with a fountain solution.

5 Another aspect is a fountain solution having any of the compositions delineated herein, including those having unsaturated fatty acid solutions of one or more poly alpha (hydroxy)aliphatic acids, and less than 10 weight % of one or more multifunctional (meth)acrylate esters, vinyl ethers, or combinations thereof, and one or more organic zirconium(4) compounds; and wherein the organic zirconium(4) compounds are 0.4 to 4 weight
10 % of the total solution.

 Another aspect is a method of printing including mixing any fountain solution delineated herein with an ink vehicle or varnish. The method includes that wherein the ink vehicle or varnish comprises 2 to 15 weight percent of one or more drying oil derived fatty acid solutions of 10-35 wt % of poly alpha (hydroxy)aliphatic acid(s); that wherein the ink vehicle or varnish
15 further comprises 1 to 7 weight % of one or more multifunctional (meth)acrylates; that wherein the fountain solution further comprises one or more organic (hydro)peroxides or one or more inorganic salts of a peracid; or that wherein the ink vehicle or varnish comprises solids, alkyds, polyesters or polyamides. The method can further include contacting the composition or ink vehicle delineated herein with water (e.g., air, water source, other moisture source) immediately
20 prior to use in printing or immediately prior to application to a printing press.

 In another aspect, the invention is a composition made by the process of combining 2 to 15 weight percent of one or more drying oil derived fatty acid solutions of 10-35 wt % of one or more poly alpha (hydroxy)aliphatic acid(s), 0.4 to 4 weight % of one or more organic zirconium(4) compounds, 1 to 7 weight % of one or more multifunctional (meth)acrylate esters,
25 vinyl ethers, or combinations thereof, and catalytic proportions of one or more inorganic salts of peracids. The process can further include combining water (e.g., air, water source, other moisture source).

 Preferred embodiments of the instant invention include those lithographic ink formulations which incorporate from about 4 to about 10 weight percent of (10 to 35 wt%)
30 solutions of short chain (2 to 6 carbon atom monomer) poly (hydroxy)aliphatic carboxylic acids

14175-006P01 /

solutions in drying oil derived fatty acids, in addition to 2 to 7 weight percent of essentially non-volatile multifunctional (meth)acrylates, and / or vinyl ethers.

Most preferred is the employment of the herein described combinations of conventional high, (preferably 100%) solids, alkyd, polyester and/or polyamide based ink vehicles, in combination with 4 to 10 weight percent of drying oil derived fatty acid solutions containing 10-35 wt % of poly(hydroxy)aliphatic acid(s), and 0.4 to 4 weight % of organic zirconium(4) compounds, preferably in combination with 1 to 7 weight % of multifunctional (meth)acrylate esters, and catalytic proportions of organic (hydro)peroxides and/or of inorganic salts of peracids (which peroxide components may be present in either the ink or fountain solution (if the last is employed), to minimize / eliminate the need to include toxic heavy metals, and or volatile solvents in the system.

In one aspect, the compositions are any of those delineated herein wherein they comprise reduced levels (relative to conventional amounts, e.g., < 1.weight % metal, about 0.05 to 0.7 weight % metal), or are devoid of, toxic heavy metals (e.g., cobalt, manganese), including in elemental or salt forms.

The introduction of said of poly (hydroxy)aliphatic acid(s), organic zirconium compound combinations as (optionally partial) solvent replacements, in otherwise conventionally formulated litho inks and varnishes not only reduces VOC emissions, minimizes/ eliminates the need for the inclusion of toxic heavy metals such as cobalt, and substantially enhances the drying acceleration effects of (organic (hydro)peroxide – reducing agent combinations (cofactor reducing agent requirements are eliminated), and / or fountain solution hydrogen peroxide addition, as taught by the prior art, but additionally provides significant performance improvements relative to the prior art. These improvements include the minimization of dot gain, and virtual elimination of ghosting (penetration of porous substrates by ink via capillary wetting), increased gloss potential, and enhanced pigment dispersion rates. The upgrades enabled via the application of the teachings of this invention permits the formulator to design reduced and /or solvent free litho inks, superior to their conventional, (alkyd-polyester-polyamide resin) based solvent borne, known art analogs.

In essence, this invention teaches the use of litho ink systems, which employ minor proportions of 2 to 15 weight percent of (10 to 35 wt.%) solutions of poly(hydroxy) aliphatic acid(s) in unsaturated fatty acids , and 0.4 to 4 weight % of organic zirconium(4) compounds

14175-006P01 /

and preferably in combination 1 to 7 weight % of multifunctional (meth)acrylate esters as optionally partial) solvent replacements in otherwise conventional lithographic inks. Said replacement, reduces VOC's, significantly enhances the drying rates of these inks and controls viscosity, and enhances the utility of low levels (10 to 5,000 ppm) of organic (hydro)peroxides and or inorganic salts of peroxy acids as cure accelerators. These accelerators may, usefully, be incorporated into the ink and /or into the fountain solution (when employed in wet plate lithography), at levels of the order of about 10 to about 5,000 parts per million (ppm). When said accelerators are activated via readily applicable techniques, e.g. chemically, thermally, and or exposure to radiation, these materials decompose to active species which affect rapid polymerization based cure of the ink

The details of one or more embodiments of the invention are set forth in the accompanying drawings and the description below. Other features, objects, and advantages of the invention will be apparent from the description and drawings, and from the claims.

DETAILED DESCRIPTION

The compositions and methods of the invention relate to coatings, and in one aspect inks. Materials that are standard and conventional in the art are suitable for use in the compositions and methods herein.

Lithographic printing is the art or process of printing from a flat plate in which the desired image is achieved by construction of said plate such that selective adhesion of the printing ink to plate occurs in the desired image area(s), followed by contact transfer of said image either directly, or indirectly to a substrate (e.g., paper, plastic, metal).

Unsaturated fatty acids are defined as materials having the composite structure $\text{HOC(O)}(\text{CR}^1\text{R}^2)_n(\text{R}^3\text{C}=\text{CR}^4)_m$, wherein m is an integer from one to about 5, wherein n is an integer from 3 to about 20, and wherein each of the various R groups (e.g., R^1 , R^2 , R^3 , R^4) is independently chosen from among hydrogen or is a monovalent hydrocarbyl group having from one to about four carbon atoms. The various (CR^1R^2) and $(\text{R}^3\text{C}=\text{CR}^4)$ need not be consecutive or in conjugation, but may be connected to each other in any order. Unsaturated fatty acids useful in the compositions and methods herein include, for example, those listed in the tables herein.

Organozirconium compounds are compounds (or complexes) having organic (i.e., carbon and hydrogen containing) functional groups bound (including covalently or through noncovalent binding interactions) to zirconium atom(s). In one aspect the compounds are those having a zirconium atom in an oxidation state of (IV). Organozirconium compounds useful in the compositions and methods herein include, for example, those listed in the tables herein.

(Meth)acrylate esters are herein defined as materials having the general structure $[RCH_2=CHC(O)O]_nR'$, wherein n is an integer larger than 1; each R is independently chosen from hydrogen, or a CH_3 group, and R' is chosen from among hydrocarbyl groups having from two to about 20 carbon atoms each, except that the number of carbon atoms in each R' must equal or exceed n . (Meth)acrylate esters useful in the compositions and methods herein include, for example, those listed in the tables herein. The compositions may have one or more (e.g., 2, 3, 4, 5 methacrylate esters) in them.

Multifunctional vinyl ethers are herein defined as organic chemicals which contain the structure $[RRC=CRO]_nR'$ wherein n is a n integer larger than 1; each R is independently chosen from hydrogen, or a CH_3 group, and R' is chosen from among hydrocarbyl groups having from two to about 10 carbon atoms each.

Inorganic salts of peracids (or peroxy acids) are herein defined as salts of acids containing the structure $(O-O^-)$, in which the cation has a positive electrical charge on an atom other than hydrogen, or carbon. Inorganic salts of peracids useful in the compositions and methods herein include, for example, those listed in the tables herein. In some aspects of the invention, the inorganic salts of peracids are used in catalytic amounts (e.g., less than about 0.5 weight percent, less than about 0.25 weight percent, less than about 0.1 weight percent, based on total weight of the composition; or between about 1 and 100,000 ppm, between about 1 and 50,000 ppm).

Organic hydroperoxides are defined as an organic compound containing the structure $C-O-O(R)$ wherein R is a chosen from among hydrogen, or a group bonded through carbon to the peroxide oxygen. Organic hydroperoxides useful in the compositions and methods herein include, for example, those listed in the tables herein.

The variety of unsaturated fatty acids, poly (hydroxy)aliphatic carboxylic acids, organo zirconium compounds, (meth)acrylate esters, vinyl ethers, and accelerators, useful in the practice of this invention is very large, however for the sake of brevity, only 10 examples of

preferred members of each class of materials are provided in Tables A through E respectively. The examples provided hereinafter are intended to be illustrative of, and not to exhaustive of nor to limit the scope of this invention. Those skilled in the art will easily be able to provide many more examples of each class of such components with minimal difficulty, and without departing from the teachings of this invention.

An ink vehicle is a combination of components, other than pigments, which is collectively suitable for ink compositions. In one aspect, the ink vehicle contains certain components that are incompatible for storage with other ink components (i.e., when in contact, an irreversible reaction takes place, which may be undesirable or may be desired to be controlled such that the reaction takes place immediately prior to, or concurrent with, use of the resulting product (e.g., ink) for printing). In such instance, one of the incompatible components is placed in the ink vehicle and the other is placed in a second ink vehicle (e.g., fountain solution) for mixing immediately prior to, or concurrent with, use. The ink vehicle can include any of the materials delineated herein, or can also include any standard ink vehicle component know in the art, including for example, solids, alkyds, polyesters or polyamides suitable for ink or printing compositions, and the like. The same material can be considered a varnish when pigments are absent from the composition. Varnishes are expressly considered one aspect of the compositions delineated herein.

The compositions herein are useful in lithographic printing applications. Such applications can be intaglio or off-set, including sheet-fed, cold-web, and heat set web printing.

The invention will be further described in the following example. It should be understood that these examples are for illustrative purposes only and are not to be construed as limiting this invention in any manner.

Examples

Table A [Poly (hydroxy) aliphatic carboxylic acids]
[Poly (hydroxy) aliphatic carboxylic acids]
constituent monomer(s)

Material Designation	
AA	hydroxy acetic acid
AB	2- hydroxy propionic acid
AC	2-hydroxy-2-methyl 3-butenic acid,
AD	2 hydroxy butyric acid
AE	2-hydroxy-6-caprolactone

14175-006P01 /

AF	ethyl 2 hydroxy propanoate
AG	methyl 2-hydroxy (2-methyl)-3-butenate
AH	hydroxy acetic acid, 3-hydroxy i-pentanoic acid
AI	2-hydroxy-3-methoxy-isobutyric acid
AJ	2 hydroxy-4-butyrolactone, 2-hydroxy propionic acid, 2-hydroxy 4-pentenoic acid

Table B [Organo zirconium (4) compounds]

Material Designation	
BA	zirconium(4) tetrakis octanolato, adduct 2 moles of (bis tridecyl) phosphite
BB	zirconium(4) tetrakis i-decanolato, adduct 2 moles of (tris lauryl) phosphite
BC	oxo zirconium(4) bis i-pentadecanoate
BD	zirconium(4) 2-propanolato, tris (bis butyl)phosphato-O
BE	zirconium(4) neodecanolato, tris (phenyl) sulfonato-O
BF	zirconium(4) t-butanolato, tris (ethyl, benzyl) phosphito
BG	zirconium(4) bis iso-hexanolato, cyclo (bis allyl) diphosphato-O,O
BH	ethylenediolato zirconium(4) cyclo (bis allyl) diphosphato-O,O
BI	1,3-propylendiolato zirconium(4) linolenate, myristate
BJ	Bis 1,4-butene-2 diolato zirconium(4) adduct 1 mole of tris (bis oleyl) phosphite

5

Table C [Multifunctional (meth)acrylates]

Material Designation	Multifunctional (meth)acrylates
CA	Tris methylol propane tris acrylate
CB	pentaerythritol trimethacrylate
CC	sorbitol tetrakis acrylate
CD	tetrakis 1,2-propylene glycol acrylate, methacrylate
CE	terphthalic acid bis 2-methacrylateoethyl ester
CF	ethoxylated(3) bisphenol A dimetacrylate
CG	acrylate terminated polybutadiene(12)
CH	Bis trimethylol propane bis acrylate, bis allyl ether
CI	zinc bis methacrylate
CJ	60% castor oil tris acrylate, 40% 1,4-cyclhexane bis methacrylate

10

Table D (Accelerators)

Material Designation	Peroxy acid salt	Incorporated into Ink (I) or Fountain Solution (F)	Preferred activation method
DA	sodium peroxy diphosphate	I or F	water.
DB	sodium perborate	I or F	water
DC	sodium persulfate	I or F	water, thermal
DD	sodium peroxy disulfate	I or F	thermal,
DE	calcium perphthalate	I	thermal, or rad.
DF	aluminum percarbonate	I	water, thermal.
DG	potassium perhenate	I	thermal, radiation
DH	t-butyl hydroperoxide	F	none required
DI	magnesium per t-butoxide	I	water, thermal
DJ	sodium peracetate	I or F	water, thermal

Example 1

5 Method for the preparation of the poly (hydroxy) aliphatic acid-fatty acid solutions.

A nitrogen blanketed pyrex glass lined vessel, equipped with an external heating-cooling jacket, a high speed disperser, and appropriate inlet and outlet ports, was charged with 150 kg of rapeseed oil fatty acid, and 75 g of 1,2,3-tris methoxy benzene . The charge was heated to and maintained, under nitrogen, at 140°C for 3.5 hr. during which period 50 kg of poly (6) caprolactone (Mw 2700, Mn 1290) (Dow Chemical Corp. Tone polymer) was incrementally added and dissolved. Under high shear. The resulting tan solution was cooled to ambient and discharged. Yield of a low viscosity of a freely flowing liquid solution (25wt%) poly 6-hydroxy caproic acid. Product designation 1A.

15 Similarly prepared in near quantitative yields were a 32% solution of poly lactic acid (Dow material) in oticca oil fatty acid (1B), and an 11% solution of poly glycolic acid (Dupont) in tung oil fatty acid (1C).

Example 2

20 Method for the preparation of the poly (hydroxy) aliphatic acid-fatty acid solutions

A nitrogen blanketed pyrex glass lined vessel, equipped with an external heating-cooling jacket, a high speed disperser, distillation column, distillate receiver, and appropriate inlet and outlet ports, was charged with 150 kg of soya been oil fatty acid, 325 g of antimony pentoxide and 75 g of 1,2,3-tris methoxy benzene . The charge was heated to and maintained, under nitrogen, at 160°C for 3.5 hr. during which period 30 kg of 4-butyrolactone, and 15 kg each of 2-hydroxy propionic acid, and 4-hydroxy 2-pentenoic acid were premixed and continuously added. After completion of the materials addition (water was observe red to distill continuously) , the reaction temperature was raised to 200°C and maintained at said temperature for @25 mm Hg vacuum for two hours. The product was recovered as a light brown modest viscosity solution after cooling to 70°C C prior to discharge. Under high shear. The resulting tan solution was cooled to ambient and discharged. Product yield was 97.7 weight %, as a low viscosity, freely flowing liquid solution (nominally 28.6 wt% terpolymer in soya oil fatty acid). Yield of distillate water [>99% Gas Chromatographic (GC) assay] was 2.16%, 98.9% of theory. Product designation 2A

Similarly prepared under comparable conditions , using the indicated reagents were a variety of analogs poly (hydroxy)carboxylic polymer solutions in unsaturated fatty acids. Cf. Table 2.

Table 2

Product Designation	Raw Material inputs/ kg.	Distillate yield kg /% of theory	Polymer Solution yield, wt/% of theory
2B	safflower oil fatty acid/130; AD/ 70; stannous octoate 0.10	<0.03 water/ *1	99.9
2C	walnut oil fatty acid/ 140; AF/ 98.3; tetra isooctyl titanate/ 0.20	38.1/ *2	100.1
2D	tung oil fatty acid / 150; AI/ 57.75;	7.72/99.5 *3	100.0
2F	oticicca oil fatty acid / 175; AE/ 15; 88% Abaq./28.4; methane sulfonic acid 0.25	8.37/ 99.4 *3	99.7
2G	linseed oil fatty acid/ 85; hemp oil fatty acid*4 / 85, AD/ 30, stannous chloride 0.40	<0.04 water/ *1	99.8

*Notes: 1) Yield of water (GC assay >99%)- present in initial raw materials'

2) Ethanol (GC 98.2%), water 0.35%- present in initial raw materials.

3) (GC assay >99% water).

4) Alkaloids depleted by 75% aq. Methyl alcohol extraction, prior to hydrolysis.

Example 3

Methods for the preparation of the rapidly drying lithographic ink vehicles demonstrating benefits of same versus conventional technology; i.e. enhanced gloss, rub resistance, and set and drying rates.

A 200 gallon water jacketed 316 ss mixing tank equipped with a 10 horsepower slow speed agitator was heated to, mixed and maintained at 50-65°C during the sequential addition of 1A, 80lb.; Ultrex 100, 240 lb., Ultrex 110 562lb. [Ultrex (aluminum gelled soya alkyd) resins were supplied by Lawter Div. Of Eastman Chemical Co.); BA 18lb, and aluminum stearate 4.5 lb. The resulting solution (3A) was evaluated for utility as a an overprint varnish. A portion of this varnish was converted to a lithograph ink by dispersion therein of 16 weight percent of a phthalocyanine blue pigment (Ciba Irgalite blue LGE). Both the ink and the varnish were evaluated versus control formulations in which the 1A, and BA were replaced by like proportions of 300°F Magie 300 ink oil (Mobil Oil), and 6% cobalt naphthenate respectively, producing inks and varnishes each having 400 rpm tack readings of 6.8, for both the test and control inks, and 5.5 and 5.7, for the control and test varnishes, respectively.

Five thousand sheets of each set of inks and overprint varnishes were each printed (full coverage), both independently and sequentially, on a Komori two color sheetfed press, @ 9,500 prints/hr. using 60 lb. Coated paper stock (international Paper Co.), and stacked in single piles maintained @ 23-23°C. Evaluation of the resulting prints showed that the ink derived from the practice of the instant invention dried 32% faster, and was 7% glossier than its conventional counterpart. (through dry time 5hr, 42 min. vs. 8 hr. 23. min.; gloss 93.5% vs 87.0%) The overprint varnish of the instant invention, dried 46% faster (7 hr. 19 min. vs. 13 hr 34 min.), and dried to a gloss 3% higher than its solvent based alternative (95.2 vs. 92.3%. The drying of the combination of ink and overprint varnish printed prints required 8hr. 34 min. vs. 14 hr. 52 min for the control system, a 59% time savings.

Furthermore the prints prepared from either the ink or varnish produced via the teachings of the instant invention could be stacked at depths of 5,000+ sheets, without offsetting, but the conventional ink and varnish (independently or as a composite) offset at stacking levels above 2,730 sheets, even after application of high doses of offset powder; whereas neither ink nor the

varnish products of the instant invention, individually, required offset powder usage. However the composite prints produced by applying both the ink and varnish of the instant invention required modest offset powder application in order to eliminate offset at stack depths above 4,200 sheets. Gloss improvement for overprint varnished blue ink was 3.5% vs. the control system (94.4 vs. 91.7).

Further improvement vs. the control formulation was achieved by heating product 3A for a period @ a temperature of from about 100 to about 170°C under nitrogen, and cooling to ambient prior to evacuation. 3AH (Through drying times for the derived ink, varnish and ink-varnish combination were reduced to 5hr. 16 min.; 6 hr. 11 min. and 6hr. 42 min. respectively upon heating the varnish/ ink vehicle @130+/-10°C for two hours prior to use. Similar treatment of the control formulations, produced no measurable improvements. Similarly produced and evaluated were a series of analogous products using a variety of ink, pigment, varnish, and vehicle components and vehicle heat treatment conditions . The resulting formulations are compiled in Table 3A. these Inks, and varnishes, were printed on a four color Man Roland 700 press, using Unigraphics 500 fountain solution Optionally modified as indicated, diluted to a conductivity of 1800-2500 siemens with deionized water . The results of these investigations are provided in Table 3B.

Table 3A

Material Identification	Formulation/wt. %	Varnish Heat history/hr./°C
3BV	tung-linseed varnish ¹ /28.8; gelled soy varnish ² /52.8; 2C/7.2; BC4.2; PE wax ⁵ /0.6 PTFE ⁶ /2.4	60-70/1.5
3BH V	tung-linseed varnish ¹ /28.8; gelled soy varnish ² /52.8; 2C/7.2; BC4.2; PE wax ⁵ /0.6 PTFE ⁶ /2.4	60-70/1.5 + 150-160/2
3B Ink	tung-linseed varnish ¹ /24; gelled soy varnish ² /44; carbon black ³ /18; Alkali Blue ⁴ /2; 2C/6; BC3.5; PE wax ⁵ /0.5 PTFE ⁶ /2	60-70/1.5
3BH Ink	tung-linseed varnish ¹ /24; gelled soy varnish ² /44; carbon black ³ /18; Alkali Blue ⁴ /2; 2C/6; BC/3.5; PE wax ⁵ /0.5; PTFE ⁶ /2	60-70/1.5 + 150-160/2
3BH1	tung-linseed varnish ¹ /24; gelled soy varnish ² /40; carbon black ³ /18; Alkali Blue ⁴ /2; 2C/6; BC/3.5; PE wax ⁵ /0.5; PTFE ⁶ /2; CC ⁷ /4.	60-70/1.5 + 150-160/2
3B Control Varnish	tung-linseed varnish ¹ /28.8; gelled soy varnish ² /52.8; Magie 300 oil ⁸ /9.0; 12% Mn octoate ⁹ /2.4; PE wax/0.6; PTFE ⁶ /2.4.	60-70/1.5 10
3B Control Ink	tung-linseed varnish ¹ /24; gelled soy varnish ² /44; carbon black ³ /18; Alkali Blue ⁴ /2; Magie 300 oil ⁸ /7.5; 12% Mn octoate ⁹ /2; PE wax/0.5; PTFE ⁶ /2.	60-70/1.5
3BH Control Ink	tung-linseed varnish ¹ /30; gelled soy varnish ² /44; carbon black ³ /18; Alkali Blue ⁴ /2; Magie 300 oil ⁸ /7.5; 12% Mn octoate ⁹ / PTFE ⁶ /2	60-70/1.5
3C Varnish	Polyamide varnish ¹⁰ /46; polyester-oil varnish ¹¹ /40 2G/11; BH/ 3	40-45/2.5 15
3C Ink	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /32 yellow pigment ¹² /14; 2G/11; BH/ 3	40-45/2.5
3C1 Ink	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /30 yellow pigment ¹² /14; 2G/11; BH/ 3; CE ⁷ /2	40-45/2.5
3C2 Ink	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /30 yellow pigment ¹² /14; 2G/11; BH/ 3; CH ⁷ /2	40-45/2.5
3CH	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /32 yellow pigment ¹² /14; 2G/11; BH/ 3.	40-45/2.5 + 110-120/ 6
3CH1	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /30 yellow pigment ¹² /14; 2G/11; BH/3; CE ⁷ /2.	40-45/2.5 + 110-120/ 6
3CH2	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /30 yellow pigment ¹² /14; 2G/11; BH/3; CH ⁷ /2.	40-45/2.5 + 110-120/ 6
3C Control Varnish	Polyamide varnish ¹⁰ /46; polyester-oil varnish ¹¹ /40 tetradecanol /7.5; 12% zirconium octoate ⁹ /3.	40-45/2.5
3CH Control Varnish	Polyamide varnish ¹⁰ /46; polyester-oil varnish ¹¹ /40 tetradecanol /7.5; 12% zirconium octoate ⁹ /3.	40-45/2.5 110-120/6
3C Control Ink	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /32 yellow pigment ¹² /14; tetradecanol /7.5; 12% zirconium octoate ⁹ /3.	40-45/2.5 25
3CH Control Ink	Polyamide varnish ¹⁰ /40; polyester-oil varnish ¹¹ /32 yellow pigment ¹² /14; tetradecanol /7.5; 12% zirconium octoate ⁹ /3.	40-45/2.5 + 110-120/ 6

- Notes: 1) Lawter-3020; 2) Lawter-Gellusoy; 3) Cabot 400R; 4) BASF, 5) Honeywell AC 540A; 6) Shamrock SST-4; 7) All acrylates, and methacrylates employed, were obtained from Sartomer Corp. 8) Pennzoil Corp. 9) OMG corp. 10) Lawter-Nypol 7; 11) Lawter Terlon 1; 12) Ciba Yellow12; 13) Blend of Lawter- Geltung 3/60% Geltung 7/40%; 14) Lenape Corp 5500.

Table 3B				
Material Designation	Set rate limited Press Speed K Impressions/hr	Ink through dry to touch time hr.	Film Gloss % @ 60°	Rubs to Film Failure ¹
3BV	12.2	17.6	94.7	>800
3BHV	12.2	14.1	94.2	>800
3B	12.8	16.4	95.1	>800
3BH	12.5	11.3	96.2	>800
3BH1	13.0	9.9	95.7	>800
3B control Var.	9.7	28.4	90.8	490
3B control Ink	9.9	22.1	89.6	470
3BH control Ink	9.8	21.7	89.9	505
3C Var.	11.9	15.8	94.7	>800
3C Ink	12.3	12.2	94.9	>800
3C1 Ink	12.5	10.2	96.1	>800
3C2 Ink	12.7	10.7	95.7	>800
3CH Ink	13.1	9.7	96.0	>800
3CH1 Ink	13.1	9.4	94.4	>800
3CH2 ink	13.3	9.8	95.1	>800
3C control Var.	9.4	22.1	91.7	540
3CH Control Var.	9.8	21.8	90.0	565
3C Control Ink	10.2	19.6	90.9	485
3C H Control Ink	10.1	19.9	92.1	460

Notes: 1) Sutherland Abrasion Test after 72 hr. cure at ambient temperature.

Similarly produced and evaluated were a series of analogous products using a variety of ink, pigment, varnish, and vehicle components and vehicle heat treatment conditions . The resulting formulations are compiled in Table 3A. these Inks, and varnishes, were printed on a four color Man Roland 700 press, using Unigraphics 500 fountain solution Optionally modified as indicated, diluted to a conductivity of 1800-2500 siemens with deionized water . The results of these investigations are provided in Table 3B.

Example 4

Utility of inorganic salts of peroxy acids, and of organic (hydro) peroxides as accelerators for the cure of the inks of the instant invention, in increasing the set limited press speed, and drying speed of the inks instant invention as compared to the response of their art counterparts.

Selected inks formulated as defined in Table 3A were printed using the same press, and conditions as were employed in Example 3, except that the ink or fountain solution employed therein were modified by the addition of the indicated ppm of an accelerator as specified. The results of this evaluation are presented in Table 4.

Table 4				
Material Designation	Accelerator / ppm In I/F	Set rate limited Press Speed K Impressions/hr	24 Hr Rubs to film failure	72 Hr. Rubs to film failure
3BV	none	12.2	570	>800
3BV	DA/ 5000/ F	>14*	>800	>800
3BV	DI/ 250/F	>14*	>800	>800
3BHV	none	12.2	685	>800
3BHV	DD/100/I	>14*	780	>800
3BHV	DJ/50/F	>14*	750	>800
3B	none	12.8	565	>800
3B	DF/30/I	13.9	710	>800
3B	DF/100/I	>14*	>800	>800
3BH	none	12.5	605	>800
3BH	DH/40/F	13.6	670	>800
3BH	DH/100/F	>14*	720	>800
3BH	DH/ 1000/F	>14*	750	>800
3B control	none	9.7	<100	490
Var.				
"	DH/1000/F	10.2	195	515

"	DI/100/F	10.4	190	525
3B control	none	9.9	110	470
Ink				
"	DF/1000/I	10.3	165	505
"	DH/1000/F	10.1	205	490
3BH control		9.8	<100	505
Ink				
"		10.0	155	590
3C Var.		11.9	390	>800
3C Var.	DA/100/I	12.9	610	>800
3C Var.	DA/100/F	13.1	635	>800
3C Var.	DB/200/F	13.0	430	>800
3C control	none	9.4	145	565
Var.				
"	DG/500/I	10.4	230	605
"	DG/500/F	10.3	250	590
3C Control	none	10.2	165	485
Ink				
"	DC/1000/F	10.4	310	540
"	DC/1000/I	10.5	300	525
"	DH/100/F	10.7	290	505
"	DH/5000/F	10.9	305	515
"	DJ/1000/F	11.1	290	540
"	DJ/1000/I	11.0	265	540

5 The compounds of this invention (including as used in compositions herein) may contain one or more asymmetric centers and thus occur as racemates and racemic mixtures, single enantiomers, individual diastereomers and diastereomeric mixtures. E-, Z- and *cis-trans*-double bond isomers are envisioned as well. All such isomeric forms of these compounds are expressly included in the present invention. The compounds of this invention may also be

10 represented in multiple tautomeric forms, in such instances, the invention expressly includes all tautomeric forms of the compounds described herein. All such isomeric forms of such compounds are expressly included in the present invention. All crystal forms of the compounds described herein are expressly included in the present invention.

15 Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. Although methods and materials similar or equivalent to those described herein can be

WHAT IS CLAIMED IS:

- 1 1. A composition comprising unsaturated fatty acid solutions of one or more poly alpha
2 (hydroxy)aliphatic acids, and less than 10 weight % of one or more multifunctional
3 (meth)acrylate esters, vinyl ethers, or combinations thereof.
4
- 5 2. The composition of claim 1, further comprising 0.4 to 4 weight % of one or more
6 organic zirconium(4) compounds.
7
- 8 3. The composition of claim 1, further comprising one or more inorganic salts of peracids.
9
- 10 4. The composition of claim 1, further comprising 0.4 to 4 weight % of one or more
11 organic zirconium(4) compounds, and one or more inorganic salts of peracids.
12
- 13 5. The composition of claim 1 comprising 2 to 15 weight percent of drying oil derived fatty
14 acid solutions of 10-35 wt % of poly alpha (hydroxy)aliphatic acid(s), 0.4 to 4 weight %
15 of one or more organic zirconium(4) compounds, 1 to 7 weight % of one or more
16 multifunctional (meth)acrylate esters, vinyl ethers, or combinations thereof, and catalytic
17 proportions of one or more inorganic salts of peracids.
18
- 19 6. The composition of claim 1, further comprising catalytic proportions of organic
20 (hydro)peroxides.
21
- 22 7. A method of printing comprising using an ink comprising the composition of claim 1.
23
- 24 8. The method of claim 7, wherein the printing comprises applying the ink to a press.
25
- 26 9. The method of claim 7, wherein the printing is lithographic printing.
27
- 28 10. The method of claim 7, wherein the printing comprises printing on paper.
29

- 30 11. A method of printing comprising using an ink vehicle or varnish comprising the
31 composition of claim 1.
32
- 33 12. The method of claim 11, wherein the ink vehicle or varnish is mixed with a fountain
34 solution.
35
- 36 13. A fountain solution comprising the composition of claim 1 and one or more organic
37 zirconium(4) compounds.
38
- 39 14. The fountain solution of claim 13, wherein the organic zirconium(4) compounds
40 comprise 0.4 to 4 weight % of the total solution.
41
- 42 15. A method of printing comprising mixing the fountain solution of claim 13 with an ink
43 vehicle or varnish.
44
- 45 16. The method of claim 15, wherein the ink vehicle or varnish comprises 2 to 15 weight
46 percent of drying oil derived fatty acid solutions of 10-35 wt % of poly alpha
47 (hydroxy)aliphatic acid(s).
48
- 49 17. The method of claim 16, wherein the ink vehicle or varnish further comprises 1 to 7
50 weight % of one or more multifunctional (meth)acrylates.
51
- 52 18. The method of claim 16, wherein the fountain solution further comprises an organic
53 (hydro)peroxides or an inorganic salt of a peracid.
54
- 55 19. The method of claim 15, wherein the ink vehicle or varnish comprises solids, alkyds,
56 polyesters or polyamides.
57
- 58 20. The composition of claim 1, further comprising one or more additional ink vehicle or
59 varnish components.
60

- 61 21. The composition of claim 20, wherein the additional ink vehicle or varnish components
62 are solids, alkyds, polyesters or polyamides.
63
- 64 22. The composition of claim 2, wherein the organozirconium compound is any of those in
65 Table B.
66
- 67 23. The fountain solution of claim 13, wherein the organozirconium compound is any of
68 those in Table B.
69
- 70 24. The method of claim 7, wherein the organozirconium compound is any of those in Table
71 B.
72
- 73 25. The method of claim 15, wherein the organozirconium compound is any of those in Table
74 B.
75
- 76 26. The composition of claim 1, wherein the poly alpha (hydroxy)aliphatic acid(s) is any of
77 those in Table A.
78
- 79 27. The composition of claim 1, wherein the multifunctional (meth)acrylate ester is any of
80 those in Table C.
81
- 82 28. A composition made by the process of combining 2 to 15 weight percent of drying oil
83 derived fatty acid solutions of 10-35 wt % of poly alpha (hydroxy)aliphatic acid(s), 0.4
84 to 4 weight % of one or more organic zirconium(4) compounds, 1 to 7 weight % of one
85 or more multifunctional (meth)acrylate esters, and catalytic proportions of one or more
86 inorganic salts of peracids.
87
- 88 29. The composition of claim 27, further comprising combining water.
89

ABSTRACT

Novel, rapidly drying, low volatile organic compound (VOC), minimal dot gain coatings, (including lithographic ink and varnish systems) are herein described. These systems dry sufficiently rapidly, that their usage eliminates ink drying speed as the rate limiting factor in most lithographic printing applications. In addition to providing enhanced drying rates as compared with their conventional counterparts, the rapid drying, low/ no VOC lithographic coating systems of the instant invention can provide the user with significant improvement in dried film rub resistance.

20497921.doc

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.